



CSI Code: 02760

No. 226

JULY 2004  
(Supersedes April 2003)

## GARDOX® Horizontal Joint Sealant

### DESCRIPTION

GARDOX Horizontal Joint Sealant is a pourable, two-component, cold-applied compound for sealing joints in concrete. Chemically reactive polymers, plasticized with coal tar, cure to a durable, rubber-like joint seal that offers a firm, smooth, non-tracking surface, retaining flexibility from -20°F (-29°C) to over +200°F (93°C). Effectively seals the joint against water infiltration and rejects incompressibles. GARDOX is resistant to jet fuels and most common solvents and chemicals.

GARDOX can accommodate a joint movement of +/-25% when a 2:1 minimum width-to-depth ratio is maintained, and proper application techniques are followed.

### USES

GARDOX Horizontal Joint Sealant is recommended for sealing horizontal joints on highways, airport runways, bridges, plaza decks and driveways. Interior uses include sealing joints in industrial floors, garage floors, airplane hangar floor joints, etc.

### SPECIFICATIONS

- FEDERAL SPEC. SS-S-200D, Type H
- FEDERAL SPEC. SS-S-195, Type H
- FAA SPECIFICATION Item P-605
- ASTM C 920, Type M, Grade P, Class 25, Use T
- Corps of Engineers CRD-C 526, Type H
- Approved by the Ministry of Transportation, Quebec

### PACKAGING

1 Gallon Unit consists of a 1/2 gallon (1.89 liters) of base and 1/2 gallon (1.89 liters) of catalyst in an imperial gallon container.

4 Gallon Unit consists of 2 gallons (7.57 liters) of catalyst in a 2-compartment 5-gallon (18.93 liter) pail.

### FEATURES AND BENEFITS

- Formulated with chemically reactive urethane polymers modified with coal tar, which cure to form a durable rubber-like joint seal
- Provides a firm, smooth, non-tracking surface in summer...retains flexibility in winter
- Requires no caulking gun or special metering equipment...blends by hand or with a slow-speed drill
- Resistant to jet fuels, most common chemicals and solvents
- Mix and pour right from the container
- Easy and economical to use

### SHELF LIFE


GARDOX should be stored in a cool warehouse. Like many top-quality, two-component sealants, GARDOX has a limited (maximum 6 months) shelf life.

NOTE: Do not open pail until ready to use, as this significantly reduces shelf life.

### COVERAGE

7.47 gal./cu.ft. (1000 L/cu.m). A 1/2" x 1/4" (12.7 x 6.3mm) joint will require 0.65 gallons/100 lineal feet (8 L/100m).

### Application Tools



Electric Drill with  
Flat-Bladed Paddle



Wooden Hand  
Paddle

*CONTINUED ON REVERSE SIDE...*

## W.R. MEADOWS, INC.

P.O. Box 338 • HAMPSHIRE, IL 60140-0338  
Phone: 847/214-2100 • Fax: 847/683-4544  
1-800-342-5976  
[www.wrmeadows.com](http://www.wrmeadows.com)

HAMPSHIRE, IL / CARTERSVILLE, GA  
YORK, PA / FORT WORTH, TX / BENICIA, CA  
POMONA, CA / GOODYEAR, AZ / MILTON, ONT.

## APPLICATION

**Surface/Joint Preparation...**Remove foreign substances, incompressibles and free water from joint opening. For proper adhesion, joints must be clean and dry. Dust, dirt and laitance should be removed prior to application.

**Priming...**GARDOX adheres well to unprimed concrete; however, the use of P/G PRIMER from W. R. MEADOWS is recommended for optimum adhesion.

**Joint Sizes...**Use in HORIZONTAL joints only. Proper joint design practices and application techniques must be followed for successful performance. GARDOX should NOT be used in joints less than 1/4" (6.35mm) wide. A 2:1 width-to-depth ratio should be maintained. However, in no case should joint sealant depth be less than 1/4" or exceed 1/2". To control sealant depth, insert W. R. MEADOWS KOOL-ROD™ Backer Rod or CERAMAR® in the joint before sealing. For larger joints, where additional support is required, use a non-asphaltic joint filler such as SEALTIGHT Cork Expansion Joint. For straight joint edges, mask off top surfaces with masking tape.

**Mixing...**THE TWO COMPONENTS ARE PRE-MEASURED TO EXACT QUANTITIES. MIX ALL MATERIAL SUPPLIED IN BOTH CONTAINERS; DO NOT MIX PARTIAL UNITS. It is absolutely essential that the catalyst and base material be thoroughly integrated and completely blended to achieve the required "chemical cure" and to function effectively.

To blend properly, pour the catalyst from the top container into the larger base material container. Then, blend thoroughly, either by hand, mixing with a wooden paddle or with a slow speed drill and flat bladed paddle used with care. In either case, the materials must be thoroughly stirred around and up and down...the sides and bottom of the container must be scraped occasionally to assure complete integration of the two components. For mechanical mixing, use a typical commercial mixing paddle. These are available in most paint and hardware stores. DO NOT USE a bent rod stock mixer.



## LIMITED WARRANTY

"W. R. MEADOWS, INC. warrants at the time and place we make shipment, our material will be of good quality and will conform with our published specifications in force on the date of acceptance of the order." Read complete warranty. Copy furnished upon request.

## Disclaimer

The information contained herein is included for illustrative purposes only, and to the best of our knowledge, is accurate and reliable. W. R. MEADOWS, INC. cannot however under any circumstances make any guarantee of results or assume any obligation or liability in connection with the use of this information. As W. R. MEADOWS, INC. has no control over the use to which others may put its product, it is recommended that the products be tested to determine if suitable for specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Specifier and user shall determine the suitability of products for specific application and assume all responsibilities in connection therewith.

**Application Method...**Pour GARDOX into joint with any clean, suitable pouring container. NOTE: GARDOX has a work life of approximately 3 hours; less at temperatures above 70°F (21°C). GARDOX will self-level and cure to a rubber-like compound in 72 hours at air and surface temperatures above 70°F (21°C). Surface may be dusted with talc or cement to reduce surface tack. Sealant will be tack-free in approximately 12 hours.

**Clean up...**Clean tools and equipment with Xylene or Toluene and remove masking tape before the sealant starts to set.

## PRECAUTIONS

GARDOX components are pre-measured to exact quantities. Mix all materials in container; do not mix partial units or dilute. Do not use GARDOX at temperatures below 40°F (4°C) or in wet joints. If expected movement is greater than +/-25%, GARDOX should not be used in this application. Do not apply GARDOX to galvanized surfaces. GARDOX may be used on steel and other non-galvanized metals only when the surfaces are first cleaned to bright metal, acid etched and P/G PRIMER is used. Do not use in joints subjected to hydrostatic pressure. Do not use in conjunction with polystyrene insulation or place in direct contact with asphaltic joint materials, unless a polyfilm interrupting strip or backer rod is used. GARDOX is not recommended for swimming pools or joints in ice rinks. GARDOX is not compatible with asphaltic joint fillers or asphaltic concrete pavements.

## HEALTH HAZARDS

Avoid contact with skin or prolonged breathing of vapors. Refer to Material Safety Data Sheet for complete health and safety information.

**FOR THE MOST CURRENT PRODUCT INFORMATION, VISIT OUR WEBSITE:  
[www.wrmeadows.com](http://www.wrmeadows.com)**